

NEUTRAL READY MIX

CMT-68

REVISED 06/24

PRODUCT DESCRIPTION & BENEFITS

SportMaster Neutral Ready-Mix is a 100% acrylic emulsion coating designed for tennis courts and other sport and recreational pavement surfaces.

USES

Tennis courts, basketball courts, pickleball courts, and other asphalt or concrete multi-purpose surfaces.

COLOR

Available in Dark Green, Forest Green, Light Green, Beige, Red, Maroon, Tournament Purple, Gray, Blue, Light Blue, Dove Gray, Ice Blue, Sandstone, Yellow, Orange, Brite Red, Black. Additional colors are available through the ColorPlus Fusion blends.

Product Data	
Type	Acrylic
Odor	Slight Ammonia
Flammability	Non-Flammable
Flash Point	None
Colors	Several Available

SURFACE PREPARATION

Pavement surface must be cleaned entirely of dust, dirt, debris and all loose materials. Repair of pavement surface defects, depressions and cracks must be completed prior to application. All repairs must be flush and smooth to adjoining surfaces.

New asphalt surfaces must cure 14 to 30 days prior to application. It is recommended to apply Acrylic Resurfacer (Technical Bulletin CMT3) as required by surface roughness and porosity to provide a smooth, dense underlayment for application of color texture and finish coats.

New concrete surfaces must cure 28 days prior to application. Ensure concrete courts are built and drained per American Sports Builders Association standards. Concrete surfaces should have a medium broom finish or similar roughened texture. They must never be steel trowelled. Etch surface with Muriatic or Phosphoric Acid and apply SportMaster Adhesion Promoter prior to application of Acrylic Resurfacer & fully tinted Neutral Ready-Mix color coating.

MIXING PROCEDURES

SportMaster Neutral Ready-Mix is ready to tint and apply. Do not add water. Add a minimum of (1) 24oz

ColorPlus Tint to each pail of Neutral Ready-Mix. Stir thoroughly prior to application. A power drill and paddle mixer are recommended. An additional 24oz ColorPlus Tint can be added for superior hiding or to achieve a ColorPlus Fusion color.

APPLICATION

Apply Ready-Mix Color with a soft rubber squeegee. Allow each coat to thoroughly dry before applying the next coat. Two coats are recommended.

IMPORTANT

Surface and air temperatures must be above 50°F (10°C) during application and for at least 24 hours after application. Stir before using. Do not apply when rain is imminent or forecast. Keep from freezing. Close container when not in use.

COVERAGE

Approximately .09 to .11 gallon per square yard per coat (80 to 100 Square Feet per gallon, per coat). Each 5 gallon pail contains 4.5 gallons of Neutral Ready-Mix, to allow for addition of ColorPlus Pigment Dispersion & mixing.

DRYING TIME

Neutral ready-Mix dries in 30 to 60 minutes under optimum drying conditions. Allow 48 hours before allowing foot traffic or play.

CAUTIONS

Do not store in direct sunlight or where temperatures exceed 100°F. Do not apply if rain is imminent or forecast. Keep from freezing. Close container when not in use. Refer to product Safety Data Sheet (SDS) for additional safety information and precautions.

WARRANTY

The statements made on this technical bulletin are believed to be true and accurate, and are intended to provide a guide for approved construction practices. Manufacturer does not make, nor does it authorize any agent or representative to make any warranty, express or implied, concerning this material as workmanship, weather, construction, equipment utilized and other variables affecting results are all beyond our control. Manufacturer warrants only that the material conforms to product specifications and any liability to the buyer or user of this product is limited to the replacement value of the product only.

NEUTRAL READY MIX

CMT-68

REVISED 06/24

In no event shall Manufacturer be liable for any injury, loss or damage, either direct or incidental, special or consequential, however arising, in connection with material or equipment furnished or work performed. Manufacturer shall not, in any manner, be liable for any defects, variations or change in condition in the substructure over which its products are installed.

Copyright © InFrasys, Inc. All rights reserved. Reproduction of any of this material is strictly prohibited.

ThorWorks Industries, Inc.
P.O. Box 2277
Sandusky, OH 44870
Phone: 1-800-326-1994
FAX: 1-419-626-5477
www.sportmaster.net